



Product Information

NEBAR WHITE

Premium Neoprene Electrical

Description A polychloroprene based bonded cork gasket. Premium quality product, mainly used in mineral oil filled transformers and switchgear.

Specification Compliance ASTM F104
Line call out F 225000 M2

Typical Properties Material tested to procedures as documented in ASTM F104

		Test Procedure
Base elastomer	NEOPRENE/NITRILE	
Thickness	0.8 to 13	
Hardness	65 to 80	ASTM D1415
Minimum tensile strength(MPa)	1.75	ASTM F152
Fluid resistance, volume swells		
ASTM 1 72 hours at 100°C	-5 to +10%	ASTM F146
IRM903 72 hours at 100°C	+5 to +30%	ASTM F146
FUEL A 22 hours ambient temperatures	0 to +15%	ASTM F146
BS148 Transformer Oil 14 days at 90°C	+10%	ASTM F146
Low temperature flexibility	-30°C	
Maximum operating temperature in fluids	105°C	
Compressibility at 2.8 N/mm ²	20 to 30%	ASTM F36
Recovery minimum	75%	ASTM F36
Normal sheet size	1.2 x 1.2	
Flexibility	5d	ASTM F147



Tiflex Limited

Tiflex House, Liskeard, Cornwall, PL14 4NB
Tel : +44 (0)1579 320808
E-mail : sales@tiflex.co.uk
Web : www.tiflex.co.uk

The information in this document is believed to be correct but does not constitute a specification. It is given in good faith but because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice. Statements of operating limits are not an indication that these values can be simultaneously applied.